## Latrobe LSS™ Vertex Tool Steel

Categories: Metal; Ferrous Metal; Alloy Steel; Carbon Steel; High Carbon Steel; Tool Steel; Air-Hardening Steel

## Material Notes:

TLS Vertex tool steel is a versatile, high-chromium, air-hardening tool steel that is characterized by a relatively high attainable hardness and numerous, chromium-rich alloy carbides in the microstructure. These carbides provide good resistance to wear from sliding contact with other metals and abrasive materials. The primary alloy carbides in Vertex are smaller than the large chromium-rich alloy carbides which are characteristic of D2 tool steel. These smaller carbides result in better impact toughness and superior fatigue properties compared to D2. The molybdenum addition in Vertex enhances the hardness of the alloy carbides, and more significantly, provides superior secondary hardening response compared to D2. Therefore, unlike D2, Vertex can be tempered at higher tempering temperatures yet still attain a hardness in excess of 60 Rockwell C. Because of the higher secondary hardness, Vertex exhibits superior wear resistance compared to D2 tempered at the higher tempering temperatures, as well as the super

Timken sold Latrobe in December 2006. They are now Latrobe Specialty Steels Co.

Vendors:

No vendors are listed for this material. Please <u>click here</u> if you are a supplier and would like information on how to add your listing to this material.

Physical Properties	Metric	English	Comments
Specific Gravity	7.68 g/cc	7.68 g/cc	
Density	7.67 g/cc	0.277 lb/in³	
Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	63.5	63.5	Air Cooled from 1052°C, 45 minutes
	64.5	64.5	Air Cooled from 1010°C, 45 minutes
	64.5	64.5	Air Cooled from 1030°C, 45 minutes
Modulus of Elasticity	207 GPa	30000 ksi	
Machinability	65 - 70 %	65 - 70 %	1% Carbon Steel
Izod Impact Unnotched	29.8 J	22.0 ft-lb	For 63 HRC
	61.0 J	45.0 ft-lb	For 54 HRC
Thermal Properties	Metric	English	Comments
CTE, linear 🌆	12.0 μm/m-°C @Temperature 38.0 - 200 °C @Te	6.67 µin/in-°F emperature 100 - 392 °F	
	13.2 μm/m-°C	7.33 µin/in-°F	
	@Temperature 38.0 - 500 °C @Temperature 100 - 932 °F		

Component Elements Properties	Metric	English	Comments
Carbon, C	1.0 %	1.0 %	
Chromium, Cr	8.25 %	8.25 %	
Iron, Fe	86.6 %	86.6 %	
Manganese, Mn	0.50 %	0.50 %	
Molybdenum, Mo	2.25 %	2.25 %	
Silicon, Si	1.0 %	1.0 %	
Vanadium, V	0.40 %	0.40 %	

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error. We also ask that you refer to MatWeb's terms of use regarding this information. Click here to view all the property values for this datasheet as they were originally entered into MatWeb.